



**PRESStige MGX - 1994**  
 .004 MIL CLEAR VINYL  
 PERMANENT 90#

**1500 FENPARK DRIVE, FENTON, MO 63026 P: 636.349.6401 F: 636.349.6402 W: MGXDIGITAL.COM E: SALES@MGXDIGITAL.COM**

- 4.0 mil clear vinyl provides excellent clarity
- Excellent printability via UV and solvent screen, UV and solvent inkjet and UV lithographic inks
- Permanent acrylic pressure-sensitive adhesive bonds well to a variety of surfaces
- Adhesive offers excellent tack, clarity and wet-out characteristics
- Backed with a 90 lb. moisture stable polycoated lay flat release liner for ease of converting
- Ideal for sheet-form converting

PRODUCT DATA	VALUE		TEST METHOD
<b>Physical Properties</b>			
Thickness (Mils[microns])	Film	4.0 (102) +/- 10%	ASTM D 3652 (Modified for use with non-tape products)
	Adhesive	.7-.8 (18-20) +/- 0.1 (3)	
	Liner	6.9 (175) +/- 10%	
Dimensional Stability (%)			Applied Shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C)
	MD	0.50	
	TD	0.50	
<b>Adhesion Properties</b>			
Ultimate Peel from	Average Oz/In	(N/m)	ASTM D 3654 (Modified for 72 hour dwell time)
Glass	53	(583)	
Expected Shear			ASTM D 3654 Method A a. 1 hour dwell b. 1 sq. in. surface c. 4 lb. load
Room Temperature (hours)	10		
Tack (gm/sq cm)	320		ASTM 2979
Expected Exterior Life	1 Year		
Service Temperature Range	-40°F to 176°F (-40°C to 80°C)		
Minimum Application Temperature	50°F (10°C)		
Storage Stability	2 years when stored at 70°F (21°C) & 50% relative humidity		

**Product Performance and Suitability Disclaimer**

All descriptive information, performance data, and recommendations for the use of Masterpiece Graphix (MGX) products shall be used as a guide only, and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute an MGX company warranty of any kind. All purchasers of MGX products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of MGX is authorized to give any warranty, guarantee, or make any representation in addition or contrary to the above.