



.004 White Vinyl/Low Tack Removable/94#

MGX-2076

1500 FENPARK DRIVE, FENTON, MO 63026 P: 636.349.6401 F: 636.349.6402 W: MGXDIGITAL.COM E: SALES@MGXDIGITAL.COM

- Low tack, removable pressure-sensitive adhesive bonds well to smooth non-tinted glass surfaces while removing cleanly
- Adhesive adheres well to an exterior glass surface over a wide range of temperatures

| PRODUCT DATA | VALUE | | TEST METHOD |
|---------------------------------|--|-----------------------------|---|
| Physical Properties | | | |
| Thickness (Mils[microns]) | | | ASTM D 3652 (Modified for use with non-tape products) |
| | Film | 3.5 (89) +/- 10% | |
| | Adhesive | 0.8-0.9 (20-23) +/- 0.1 (3) | |
| | Liner | 6.9 (175) +/- 10% | |
| Dimensional Stability (%) | | | Applied shrinkage: 24 hour dwell time on aluminum panel then 24 hours at 160°F (71°C) |
| | MD | 0.50 | |
| | TD | 0.50 | |
| Adhesion Properties | | | |
| Ultimate Peel from | Average Oz/In | (N/m) | ASTM D 903 (Modified for 72 hour dwell time) |
| Non-tinted Glass | 13 | (143) | |
| Tack (gm/sq cm) | 70 | | ASTM 2979 |
| Expected Exterior Life | Two years | | |
| Service Temperature Range | -20°F to 176°F (-29°C to 80°C) | | |
| Minimum Application Temperature | 50°F (10°C) | | |
| Storage Stability | 2 years when stored at 70°F (21°C) & 50% relative humidity | | |

Product Performance and Suitability Disclaimer

All descriptive information, performance data, and recommendations for the use of Masterpiece Graphix (MGX) products shall be used as a guide only, and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute an MGX company warranty of any kind. All purchasers of MGX products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of MGX is authorized to give any warranty, guarantee, or make any representation in addition or contrary to the above.