



MGX-2929

.004 White Vinyl/Permanent/75# Scored
13x19

1500 FENPARK DRIVE, FENTON, MO 63026 P: 636.349.6401 F: 636.349.6402 W: MGXDIGITAL.COM E: SALES@MGXDIGITAL.COM

Facestock: A 4 mil white vinyl with polymeric plasticizers, formulated to provide optimum performance with pressure sensitive adhesives.

Type:	Film	Basis Weight:	N/A		Federal Regulation Approval	
Caliper:	4.00 mil	Tensile:	MD: 3900 lb/in	CD: 3800 lb/in	Heavy Metals:	Yes
Opacity:	90.0 %	Tear:	MD: 100 grams	CD: 100 grams	Toy Safety:	Yes
Brightness:	N/A	Elongation:	MD: 500%	CD: 240%	Indirect Food:	No
					Direct Food:	No

Adhesive: An aggressive rubber based adhesive showing high initial tack with high shear and high ultimate adhesion. It has fair plasticizer, UV and solvent resistance. This is not recommended for water immersion. This adhesive has good adhesion to most substrates.

Coat Weight:	Heavy	Federal Regulation Approval		Typical Adhesion Values	
Adhesive Type:	Permanent Latex	Heavy Metals:	Yes	Stainless Steel:	
Shear:	136 minutes	Toy Safety:	Yes	180° Peel:	5.6 lb/in
Minimum Application Temperature:	35° F	Indirect Food:	Yes	Loop Tack:	3.90 lb/in□
Service Temperature:	-65° F to 200° F	Direct Food:	No	Glass:	
ACTS Approval:	N/A			180° Peel:	2.8 lb/in
				Polyethylene:	
				180° Peel:	5.6 lb/in
				Corrugated:	
				180° Peel:	5.8 lb/in
				Painted Metal:	
				180° Peel:	5.0 lb/in

Release Liner: A bleached kraft which has been silicone coated one side to give a controlled release. This paper has high internal strength to withstand all conventional processing operations including die-cutting and butt-cutting. The back is scored for the purpose of bending, creasing, folding or tearing.

Basis Weight:	69 lb/ream	Tensile:	MD: N/A	CD: N/A
Caliper:	4.6 mil	Tear:	MD: N/A	CD: 100 grams

Product Performance and Suitability Disclaimer

All descriptive information, performance data, and recommendations for the use of Masterpiece Graphix (MGX) products shall be used as a guide only, and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute an MGX company warranty of any kind. All purchasers of MGX products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of MGX is authorized to give any warranty, guarantee, or make any representation in addition or contrary to the above.